

VITROPERM[®] 270

NOMINAL ALLOY COMPOSITION

Alloy	Fe	Ni	Cu	Nb	Si	B	
VP 270	Balance (79.7)	5.8	1.0	5.4	6.4	1.7	(wt-%)
	71.8	5.0	0.8	2.9	11.5	8.0	(at.-%)

MAGNETIC PROPERTIES¹

Property	VP 270
Saturation polarization (as cast / amorphous @ 20 °C)	1.24 T
Polarization (nanocrystalline @ 20°C, 500 A/m)	1.32 T
Saturation magnetostriction (as cast / amorphous)	25 ppm
Saturation magnetostriction (nanocrystalline)	6 - 7 ppm
Permeability (transverse field annealing ½ h @ 540 °C)	5,100
Permeability (transverse field annealing ½ h @ 560 °C)	4,700
DC coercivity (F annealed / flat hysteresis loop)	> 3 A/m
Curie temperature	~ 600 °C

PHYSICAL PROPERTIES¹

Property	VP 270
Mass density (as cast / amorphous)	7.30 g/cm ³
Mass density (nanocrystalline)	7.50 g/cm ³
Electrical resistivity	1.15 μΩm
Coefficient of thermal expansion (20 - 100 °C)	8 · 10 ⁻⁶ /K
Crystallization temperature	~ 480 °C

AVAILABLE DIMENSIONS

Property	Value	Unit
Thickness (computed average thickness from weight)	18 ± 3	μm
Widths slit to width (others on request)	3.0 ... 46.0 ± 0.15	mm
Widths width as cast (others on request)	30.0 ... 50.0 ± 0.5	mm

¹ Typical values, not part of a specification

VACUUMSCHMELZE CHINA MAGNETICS

Shanghai Sales Office
Room 06, 19F
Zhongrong Hengrui International Plaza
620 Zhangyang Road, Pudong District
Shanghai, PRC 200122
Phone +86 21 58 31 98 37
Fax +86 21 58 31 99 37
vac_china@vacuumschmelze.com

VACUUMSCHMELZE GMBH & CO. KG

Grüner Weg 37
D 63450 Hanau / Germany
Phone +49 6181 38 0
Fax +49 6181 38 2645
info@vacuumschmelze.com
www.vacuumschmelze.com

VAC MAGNETICS LLC

2935 Dolphin Drive
Suite 103
Elizabethtown, KY 42701
Phone +1 270 769 1333
Fax +1 270 769 3118
info-usa@vacmagnetics.com

Published by VACUUMSCHMELZE GmbH & Co. KG, Hanau, Oktober 2021
© VACUUMSCHMELZE GmbH & Co. KG 2021. All rights reserved.

® is a Registered Trademark of VACUUMSCHMELZE GmbH & Co. KG



ADVANCED MAGNETIC SOLUTIONS